


AeroRigid™ 291A

Aluminum Panel for Aircraft Interiors

The AeroRigid™291A is a sandwich panel made with aluminum facings and aluminum honeycomb core, designed for use in aircraft interiors.



Features

- High strength-to-weight ratio
- Good cost effectiveness
- Service temperature: up to 180°F

Applications

The AeroRigid™ 291A is designed for use in aircraft interior structural and nonstructural applications such as monuments, shelving, partitions, bulkheads and galleys.

Availability

Thickness: 0.125", 0.250", 0.375", 0.500", 0.750" and 1.000"
Facing: 0.020"
Width: Standard 48" (Maximum 60")
Length: Standard 96" (Maximum 144")

Construction

Facing : 2024-T3 CLAD
Honeycomb Core: 5052 AL 1/4" Cell, 3.4 lbs/ft³
Adhesive: Epoxy

Typical Performance Properties

Part Number	Panel Thickness inch	Panel Wight lbs/sf [Mean]	Long Beam Flexural Load at Failure lbs [Mean]		Long Beam Flexural Facing Stress psi [Mean]		Short Beam Core Shear psi [Mean]		Climbing Drum Peel in-lbs/in [Mean]	Stabilized Core Compression psi [Mean]	FAA Allowables *1
			L	W	L	W	L	W			
AR291A-A0125	0.125	0.68	63 ^{*2}	60 ^{*2}	45,041	43,028	346	271	15	549	Good
AR291A-A0250	0.250	0.72	143	138	46,674	44,926	293	181	15	395	Good
AR291A-A0375	0.375	0.75	224	210	47,199	44,355	266	162	15	372	Good
AR291A-A0500	0.500	0.79	305	296	47,449	46,077	247	151	15	365	Good
AR291A-A0750	0.750	0.86	474	439	48,184	44,829	172	137	15	364	Good
AR291A-A1000	1.000	0.92	627	576	48,367	45,347	130	128	15	362	Good

*1 Meet FAA allowable per FAR 25.853 Appendix F, Part I - 60 second vertical ; Part IV - Heat Release; Part V - Smoke Emission

*2 Maximum values without failure

Note: Above figures reflect typical values and should not be used as design specifications.

CONTACT FOR MORE INFORMATION

SHOWA AIRCRAFT INDUSTRY CO., LTD.
Tokyo Sales Office
600 Tanaka-cho, Akishima-shi, Tokyo 196-8522, Japan
Phone: +81-42-541-8883
Fax: +81-42-541-8899
e-mail: honeycombsales196@showa-aircraft.co.jp

SHOWA AIRCRAFT USA INC.
8620 154th Ave. NE, Suite 140
Redmond, Washington 98052, USA
Phone: +1-425-202-7238